

THOMSON

DELPHION

RESEARCH

PRODUCTS


INSIDE DELPHION

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: Create new Work File View: [INPADOC](#) | Jump to: [Top](#)**Title: JP2000302522A2: PRODUCTION OF FIBER REINFORCED CEMENT BOARD****Country: JP Japan****Kind: A2 Document Laid open to Public inspection I****Inventor: WATANABE KOICHI;
YAMADA HIDEKI;****Assignee: MATSUSHITA ELECTRIC WORKS LTD**
[News, Profiles, Stocks and More about this company](#)**Published / Filed: 2000-10-31 / 1999-04-21****Application
Number: JP1999000114223****IPC Code: C04B 28/18; B28B 1/52; B28B 11/24; C04B 40/02;****ECLA Code: C04B40/02D;****Priority Number: 1999-04-21 JP1999000114223****Abstract:** PROBLEM TO BE SOLVED: To obtain a board having excellent freeze damage resistance, strength and dimensional stability and having a low specific gravity by specifying the molar ratio of CaO/amorphous silica of a raw material composition containing cement, silica and reinforcing fibers and subjecting the compsn. to a precuring, successively to an autoclave curing.

SOLUTION: The molar ratio of the CaO/amorphous silica of the raw material composition is specified to 3.0 to 12.0. A silica composition is preferably fly ash and the ratio thereof is preferably 10 to 60 pts.wt. (hereafter 'parts') to 100 parts cement. The reinforcing fibers include pulp fibers and the content thereof is preferably 12 to 17 parts per 100-parts cement. The precuring in a saturated steam state preferably involves the execution of secondary curing for 4 to 72 hours at 60 to 100°C after primary curing. The primary curing is preferably executed within 10 hours at a temperature below 60°C. The autoclave curing is preferably executed for 2 to 16 hours at 160 to 180°C. Consequently, the cement board having the specific gravity of about 1.20 to 1.45 is obtained.

COPYRIGHT: (C)2000,JPO

Family: None**Other Abstract
Info: CHEMABS 133(24)339036M CHEMABS 133(24)339036M DERABS
C2001-095176 DERABS C2001-095176**[View
Image](#)

1 page

**BEST AVAILABLE COPY**